

Technical Data Sheet

ADSIL™ Neutral

One component adhesive silicone sealant

Features & Benefits

- Neutral cure product without any objectionable acetic fumes
- Cures to a strong, flexible seal capable of withstanding movement in and around the joint
- Adheres to a range of common building material and finishes
- Non-slumping overhead joints
- Easy to use-one part, no mixing required
- Can be applied in any seasons
- Resistance to weathering, ultra-violet radiation,vibration,moisture,ozone,temperature,extremes,airbone pollutants, cleaning detergents and many solvents

Applications

- All general purpose sealing /bonding applications in construction like aluminum window perimeter sealing.ACP panel pasting and groove filling, bath tub and basin sealing, industrial roofing, cold storage panel joints, telecom shelters, mirror fixing, shower cubicals,dust free room etc
- Many industrial applications of sealing/bonding where acetic acid fumes are not desirable in confined area working like air conditioning ducting sealing, solar heater panel sealing,busbody etc

Colour

- Clear,White,Black and Grey

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Test ¹	Property	Unit	Result	
	Color		Clear	Black, White, Grey
Uncured – 23°C, 50% R.H.				
ASTM D 2202	Flow(Sag or Slump)	mm	0	0
CTM 0098	Tack-Free Time	min	Max 20	Max 20

CTM 0364	Extrusion Rate	g/min	200-450	200-400
ASTM D 1475	Specific Gravity	g/ml	0.95-1.0	≥1.40
Cured 7 days – 23°C, 50% R.H.				
ASTM D2240	Shore A Hardness	points	20-30	30-40
ASTM D412	Tensile Strength	Mpa	≥0.8	≥1.0
ASTM D412	Elongation at Break	%	≥400	≥400

1. ASTM – American Society for Testing and Material
2. CTM-Corporate Test Method

Description

ADSIL Neutral RTV Silicone Sealant is cost effective, multipurpose, neutral cure silicone sealant offering long term durability in a range of general sealing, general glazing, waterproofing and trade applications. Non-corrosive to concrete, brick and metals

How To Use

Preparation

- Clean all joint surfaces. Surfaces must be clean, dry and sound. Remove loose debris and/or old sealant. General recommendations are: For non-porous surfaces: Solvent wipe the joint surfaces using a non-oily solvent such as methyl ethyl ketone, white sprits or mineral turpentine on a clean white lint-free cloth to remove any oils and contaminants. Immediately wipe with a second dry cloth to remove any traces of solvent and contamination For Porous surfaces such as concrete: Wire brush or abrade the surfaces to remove loose debris, old paint and other contaminants. Remove dust with an oil-free compressed air blast and/or high pressure water blast. Allow to dry before sealing. If necessary solvent wash and allow to dry

Application Method.

- Mask adjacent surfaces with masking tape. Masking will ensure a clean, neat appearance and reduce clean up by protecting surrounding areas from excess sealant.
- Cut tip off the cartridge. Cut nozzle at 45° angle to the desired shape and size. Screw nozzle onto cartridge. Place cartridge in caulking gun. Air-operated or hand-operated caulking guns can be used. Apply sealant into the base of the joint so that it completely fills the joint, wetting both sides. Do not simply lay a bead on the surface as the sealant will not penetrate the joint under its own weight.
- Tool the surface of the joint immediately after sealant application to provide a smooth even finish and to ensure the sealant wets the sides of the joint. Tooling should be completed in one continuous stroke before the sealant forms a skin (ie; within the working time). A tool with a convex profile is

recommended to keep the sealant within the joint. When sealing horizontal joints tool the sealant so that any liquids (eg. rain water, cleaning solutions) do not collect and pool on top of the sealant. Do not use soap or water as tooling aids. Remove masking tape immediately after tooling and before the sealant skins. After a skin has formed, do not disturb the joint for 48 hours. Avoid contact with various cleaning agents or solvents (eg. bleach) whilst sealant is curing. Uncured sealant can best be cleaned from tools using commercial solvents such as xylene, toluene or methylethyl ketone. Mineral turpentine will suffice if available. Observe proper precautions when using flammable solvents. On porous surfaces allow sealant to cure before removing by abrasion.

- Cured sealant is not soluble and must be trimmed with a blade, avoid undercutting the seal. Sealant releases ethyl methyl ketoxime and ethanol during cure. Once cured this odour disappears. Fully cured sealant is not hazardous.

**Handling
Precautions**

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

**Usable Life And
Storage**

When stored at or below 30°C (86°F) in the original unopened containers, ADSIL Neutral has a usable life of 12 months from the date of manufacture.

**Packaging
Information**

This product is available in 300ml Cartridges & 200KG Drum

For more information visit our website-www.adarshachemicals.com

ADARSHA

Adarsha Specialty Chemicals Pvt Ltd
#25/3-2. Unit No D3. Rathod Vatika,
1st Stage, Industrial suburb,
Yeshwanthpur, Bangalore-560022
omkarmurthy@adarshachemicals.com